

## PRODUCT DESCRIPTION

GPS-1188 is a two component, 100% solids, 1A:1.88B mix ratio modified polyurea liner system for metal, concrete, wood and fiberglass surfaces. It offers good chemical resistance and low temperature flexibility. It is applied with low pressure equipment and it can be built up in a single application, multi-pass method. This product is great as a tough elastomeric liner for pick-up truck beds, boats, waterproofing, cargo holds, horse trailers and other vehicles.

## TYPICAL PROPERTIES

**Solids, by Volume** \_\_\_\_\_ 100%  
**Mix Ratio** (by volume) \_\_\_\_\_ 1A:1.88B  
**Number of Coats** \_\_\_\_\_ One coat multi-pass  
**Pot Life** \_\_\_\_\_ 12-16 seconds @ 77°F (25°C)  
**Tack Free Time @ 150 mils** \_\_\_\_\_ 40-60 seconds  
**Recoat Time** \_\_\_\_\_ 6-12 seconds  
**Density (A&B combined)** \_\_\_\_\_ 9.2 lbs/gal  
**Elongation (ASTM D-412)** \_\_\_\_\_ 200 ± 50%

**Tear Resistance (ASTM D-624)** \_\_\_\_\_ 175-200 pli  
**Hardness (ASTM D 2240)** \_\_\_\_\_ 91-93 Shore A  
**Service Temperature** \_\_\_\_\_ -20°F to 200°F  
**Viscosity (@ 80°F)**  
Side A \_\_\_\_\_ 700-900 cps  
Side B \_\_\_\_\_ 700-900 cps  
**Tensile (ASTM D-412)** \_\_\_\_\_ 1300 ± 200 psi

## PACKAGING, STORAGE AND SHELF LIFE

One 55 gallon drum net content 500 lbs. of Side-A (Isocyanate side) and two 55 gallon drum net content 450 lbs. each drum of Side-B (Resin side).

Material has a shelf life of 12 months after the date of manufacture if properly stored. Refer to Batch Number on product label for date of manufacture.

## SAFETY PRECAUTIONS

**GPS- 1188 IS FOR INDUSTRIAL USE ONLY.** Avoid contact with eyes, and skin; do not inhale or ingest. When working with this material wear goggles, rubber gloves and a respirator. When spraying in a confined area, also wear a fresh air hood and make provision for forced ventilation. Refer to MSDS regarding individual components.

## MIXING

GPS-1188 may not be diluted under any circumstances. Thoroughly mix GPS-1188 Part-B (Resin side) with air driven power equipment until a homogeneous mixture and color is obtained.

## APPLICATION GUIDELINES

Both Side-A and Side-B materials should be preconditioned to 75-80°F before application.

Recommended surface temperature must be at least 5°F above the dew point. GPS-1188 should be applied using plural component, low pressure spray mixing equipment. The simple spray equipment can have a single motor driving two separate fixed ratio proportioning pumps. Side-A and Side-B are pumped separately to a static mixing tube for air assisted or airless spray. It is recommended to use a x 24 element mixing wand/Static spiral mixer for proper mixing.

## **WARRANTY**

GLOBAL POLYMER SOLUTIONS warrants this product to be free of defects in material and workmanship. GLOBAL POLYMER SOLUTIONS's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at GLOBAL POLYMER SOLUTIONS's option, to either replace the products not conforming to this Warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by the Buyer to GLOBAL POLYMER SOLUTIONS in writing within (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify GLOBAL POLYMER SOLUTIONS of such nonconformance as required herein shall bar Buyer from recovery under this Warranty.

GLOBAL POLYMER SOLUTIONS makes no other warranties whether express, implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall GLOBAL POLYMER SOLUTIONS be liable for consequential or incidental damages.

Any recommendations or suggestion relating to the use of the products made by GLOBAL POLYMER SOLUTIONS, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by buyers having requisite skill and know-how in the industry, and therefore it is for Buyer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

## **LIMITATION OF LIABILITY**

GLOBAL POLYMER SOLUTIONS's liability on any claim of any kind, including claims based upon GLOBAL POLYMER SOLUTIONS's negligence or strict liability, for any loss or damage arising out of, connected with, or resulting from the use of the products, shall in no case exceed the purchase price allocable to the products or part thereof which gives rise to the claim. In no event shall GLOBAL POLYMER SOLUTIONS be liable for consequential or incidental damages.